




德安泰材料科技
TECRON MATERIAL TECHNOLOGY

RECYLCED FABRIC	TECHNICAL DATA	TEST METHOD
Article Name	Orange FR Recvcd CVC twill fabric	
Article No.	R-TSHM-0014-FR1	
Width	143.3cm(+2/-1cm)	ISO 22198:2006
Weight	209asm(±5)	ISO 3801:1978
Composition	cotton , recvcd polyester	
Finishing	FR	

PERFORMANCE		
Dimensional Change	<3%	ISO 5077"2007 After 5×cleaning cycles at 75 °C ISO 15797:2018
Flammability Test	Compliant with Requirement	EN ISO 16112:2017
Tensile strength	Warp:816N,Weft:426N	GB/T3923
Tear Strength	Warp:19N,Weft:17N	ISO GB/T3917
Color fastness to dry rubbing	4	GB T3920-2008
Color fastness to wet rubbing	2 - 3	GB T3920-2008
Washing Recommendations		EN-ISO 6330, 6N 60 °C: 2013

CONTACT US AT:

TECRON MATERIAL TECHNOLOGY

上海市青浦区沪青平公路2008号竞衡大业广场1718室 邮编 201702

Room 1718, JH Plaza, No. 2008 Huqingping Road, Qingpu District, Shanghai 201702, China, P. R.

Phone电话: +86 21 6976 1398 Email邮箱: info@tecronmaterial.com Website网站: www.tecronmaterial.com

All listed test data and ranges represent typical values. All test data and ranges are the result of multiple tests unless otherwise stated. To the best of our knowledge, the information contained herein is accurate. However, Tecron Meterial Technology assumes no liability whatsoever for the accuracy or completeness of the information contained herein