




RECYLCED FABRIC	TECHNICAL DATA	TEST METHOD
Article Name	FR VISCOSE WITH ARAMID KNITTED JERSEY	
Article No.	A-TSHM-001-R	
Width	148cm(+2/-1cm)	ISO 22198:2006
Weight	145gsm(±5)	ISO 3801:1978
Composition	FR viscose , aramid, antistatic	
Finishing		

Physical Performance		
Dimensional stability to washing	≤5%	ISO 5077:2007 After 5×cleaning cycles at 75 °C ISO 15797:2018
Formaldehyde Content (mg/kg)	NO	GB/T 2912.1-2009
PH value	5.8	ISO 3701-2005
Colour Fastness to Washing	4-5	ISO 105-C06
Colour Fastness to Perspiration	4-5	ISO 105-X12
Colour Fastness to Rubbing	4-5	ISO 105-E04
Pilling Resistance	3	ASTM D3514-1981
Flammability	Compliant	EN ISO 11612 A1 A2,
Electrostatic Resistance	Compliant	EN 1149-3:2004
Washing Recommendations		EN-ISO 6330, 6N 60 °C: 2013

CONTACT US AT:

TECRON MATERIAL TECHNOLOGY

上海市青浦区沪青平公路2008号竞衡大业广场1718室 邮编 201702

Room 1718, JH Plaza, No. 2008 Huqingping Road, Qingpu District, Shanghai 201702, China, P. R.

Phone电话: +86 21 6976 1398 Email邮箱: info@tecronmaterial.com Website网站: www.tecronmaterial.com

All listed test data and ranges represent typical values. All test data and ranges are the result of multiple tests unless otherwise stated. To the best of our knowledge, the information contained herein is accurate. However, Tecron Material Technology assumes no liability whatsoever for the accuracy or completeness of the information contained herein