




| Product Name                    | Modacrylic Tencel FR & Antistatic Jersey Fabric                                     | Reference Standard/ Test Method                 |
|---------------------------------|---|---|
| Product Code                    | T-TSHM-013-RB   |   |
| Width Cuttable                  | 165cm (+2/-1cm)   | ISO 22198:2006                                  |
| Gram Weight                     | 185gsm (±5)   | ISO 3801:1978                                   |
| Fibre Composition               | Modacrylic/Lyocel/FR Fiber /Carbon  |   |
| Construction Pattern            | Knitted   |   |
| Colour                          | Royal Blue(Grey)  |   |
| Dimensional Stability           | ≤±3%  | ISO 5077:2007 After 5 * Cleaning Cycles at 40°C |
| Formaldehyde content (mg/kg)    | Not Detectable  | ISO 14184.1:2011                                |
| pH Value                        | 6.5   | ISO 3701:2005                                   |
| Color fastness to water         | 4-5   | ISO 105-E01:2013                                |
| Color fastness to perspiration  | 4-5   | ISO 105-E04:2013                                |
| Color fastness to washing       | 4-5   | ISO 105-C06:2010                                |
| Color fastness to rubbing (Dry) | 4-5   | ISO 105-X12:2016                                |
| Color fastness to rubbing (Wet) | 3-4   | ISO 105-X12:2016                                |
| Color fastness to washing       | 4-5   | ISO 105-C06:2010                                |
| Pilling resistance              | 3   | ISO 12945-1:2000                                |
| Flammability                    | Compliant   | EN ISO 11612:2015 A1 A2                         |
| Electrostatic Resistance        | Compliant   | EN 1149-3:2004                                  |
| Wash Recommendations            |  | EN ISO 6330:2013, 4N 40°C                       |

**CONTACT US AT:**

**TECRON MATERIAL TECHNOLOGY** (A Division of Shenzhen Tecron Safety Co., Ltd.)

Room 1718, JH Plaza, No. 2008 Huqingping Road, Qingpu District, Shanghai 201702, China, P. R.

Phone: +86 21 6976 1398 Email: info@tecronmaterial.com

Website: www.tecronmaterial.com; www.tecronmaterial.com

*All the data listed in the above table are either individual test results or the most typical indicative parameters to the best of our knowledge. Owing to existence of possible variation or deviation from case to case, the data and information shown in the table is only for your reference. However, Tecron Material Technology or Shenzhen Tecron Safety assumes no liability for the accuracy or completeness of the information.*