



Product Name	UHMWPE BONED WITH NYLON	Reference Standard/ Test Method
Product Code	U-TSHJ-001	
Width Cuttable	145cm (+2/-1cm)	ISO 22198:2006
Gram Weight	154gsm (± 5)	ISO 3801:1978
Fibre Composition	UHMWPE/NYLON	
Colour	Green	
Dimensional Stability	$\leq \pm 3\%$	ISO 5077:2007 After 5 * Cleaning Cycles at 40°C
Breaking Strength (N)	Warp 2057; Fill 1116	ISO 13934-1:2013
Tear Strength (N)	Warp 192; Fill 105	ISO 13937-2:2000
Formaldehyde Content (mg/kg)	Not Detectable	ISO 14184.1:2011
Bacteriostatics	Compliant	ISO 105-C06: 1994
Cleaning Recommendations		EN ISO 6330:2013, 4N 40°C

CONTACT US AT:

TECRON MATERIAL TECHNOLOGY (A Division of Shenzhen Tecron Safety Co., Ltd.)

Room 1101-1102, Building B, No.628 Huaxu Road, Xujing Town, Qingpu District, Shanghai, 201702, China, P. R.

Phone: +86 21 6976 1398 Email: info@tecronmaterial.com

Website: www.tecronmaterial.com; www.tecron-safety.com

All the data listed in the above table are either individual test results or the most typical indicative parameters to the best of our knowledge. Owing to existence of possible variation or deviation from case to case, the data and information shown in the table is only for your reference. However, Tecron Material Technology or Shenzhen Tecron Safety assumes no liability for the accuracy or completeness of the information.